



**TEST REPORT - NATURAL RUBBER 70**

		COMP MFR	R7001B 8063
Complies to	ASTM D2000 M2AA707 A13 B13 F17		
Colour	BLACK		
Temp range	-40C TO +80C		
Heat Aging	70C FOR 70 HRS		
	Hardness Change	+/- 15	+ 2
	Tensile Strength Change	+/- 30	- 17
	Elongation Change	- 50	-3
Compression Set	70C FOR 22 HRS	50	11
Low Temp Brittleness	3 min at -40 C	NON BRITTLE	

Please note that these results are for reference purposes only and Supaseal makes no warranty, expressed or implied, that parts manufactured from this compound will perform satisfactorily in the customer's application. It is the customers responsibility to test and evaluate parts prior to use.

Tel: 01858 434141

Fax: 01858 434717

e-mail: [sales@supaseal.co.uk](mailto:sales@supaseal.co.uk)